

Product Name:	Biodegradable plastic injection material
Model Number:	CCBM03
Machining type:	Injection molding
Biological base material:	PBAT+PLA
Density:	1.25g/cm ³
Melt index:	6-8g/10min
Impact strength:	8-12kj/m ³
Heat distortion temperature:	80-100℃
Processing temperature:	170-195℃
Use:	fine tableware injection molding
Packing:	25kg a bag
Color:	milk white
Package:	bag+Master Carton
MOQ:	1ton
Certificate:	EN13432/ASTM D6400/SGS/FDA/REACH/RHOS
Compostability:	Biodegradable & compostable
Sample Charge:	Please contact the person in charge
Payment:	T/T
Shipment Term:	FOB/CFR/CIF...
Lead Time:	7-15 days, depends on ordered quantity